

Emcoril Protect M

Concrete curing for non-trafficable surfaces in general concrete constructions

Product Properties

- Ready-to-use water-based paraffin dispersion
- Exceptionally high level of evaporation protection especially for hot summer temperatures
- Strong barrier effect (SM > 85 %)
- Facilitates optimum hydration progress in the concrete layer close to the surface
- Minimises the occurrence of early shrinkage cracks
- Decreases the rate of carbonation
- Low emission level acc. to AgBB
- Dries rapidly
- Solvent-free
- Film-forming
- Apply by spraying
- Tested acc. to ASTM C 309, Type 1, Class A
- Certified to TL NBM-StB 09, Type BM

Areas of Application

- Curing of freshly laid concrete to German code TL NBM-StB 09, Type BM
- Evaporation protection for general concrete construction, e.g. concrete slabs, walls, foundations and columns
- Evaporation protection for non-trafficable surfaces without grip requirements
- Evaporation protection for indoor and outdoor concrete
- For application on fresh to matt-damp concrete*

Application Instructions

General

Emcoril Protect M forms a protective film on the concrete surface, extensively inhibiting evaporation of the water during the decisive hardening phase. Its strong barrier effect ensures optimum hydration progress in the concrete layer close to the surface. As a result, good strength development is achieved and the occurrence of early shrinkage cracks is minimised.

Any puddles and pools of water must be removed before application.

Application Methods

Emcoril Protect M is sprayed onto the matt-damp, fully compacted and rubbed or smoothed concrete surface to produce an even coating. The quantity applied must be as specified.

Emcoril Protect M can be applied using MC-Spezialspritze or standard commercial pressure sprayers (including tree sprayers) equipped with flat jet nozzles (e.g. MESTO 1421 flat-jet nozzle 80-01 E). MC-Pump 1 canister sprayer or with the MC-Pump 2 drum sprayer may also be used for the application work. When using these devices, ensure compliance with the MC-Pump equipment

planner.

To ensure even spray application, the distance between nozzle and concrete surface during spraying should be approx. 0.5 - 1 m.

Overcoating / Overworking

According to TL NBM-StB 09, curing/evaporation protection agents of type BM form a film which remains present and can only be removed, if required, by special measures. If the surface coated with Emcoril Protect M is to be subsequently coated with paint, sealants, coatings, etc., the film must be completely removed. Cold high-pressure water cleaning or blasting with solid abrasives is suitable for this purpose.

Further Information

The minimum concrete curing time depends on the exposure class, surface temperature and strength development. The relevant information can be determined from EN 13670/DIN 1045-3. However, Emcoril Protect M does not provide thermal protection (e.g. from cooling, high temperatures or extreme temperature changes).



Technical Properties of Emcoril Protect M

Characteristic	Unit	Value*	Comments
Density	kg/dm ³	approx. 0.98	
Barrier coefficient	%	approx. 86	acc. to TL NBM-StB 09
Water retention	kg/m ²	0.54	after 72 h acc. to ASTM C 309
Consumption	g/m ²	150 - 200	
Drying time	hours	approx. 4.5	Tack-free
Viscosity	s	11	Kinematic acc. to DIN 53211 - 4 mm
Application conditions	°C	≥ + 5 - ≤ + 30	Air, substrate and material temperature

Product Features of Emcoril Protect M

Self-monitoring	EN ISO 9001
Third-party monitoring	MPA Karlsruhe
Equipment cleaning agent	Water
Colour	Milky white
Form	Liquid
Packaging	30 kg canisters 200 kg drums 1,000 kg containers (on request)
Storage	Keep free from frost! Shelf life 12 months if stored dry in original containers
Disposal	In the interest of the environment, please ensure the containers are empty and residue-free prior to appropriate disposal.

* As soon as the visible film of water has disappeared and the concrete surface appears matt-damp.

** All technical values are laboratory results determined at +20 °C and 50 % relative humidity.

Safety Advice

Please note the safety information and advice given on the packaging labels and safety data sheets.
GISCODE: NBM 10; water hazard class: 1

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 12/18. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.